



Iron Pipe Size (IPS) and Dimension Data

ASTM D-3035-03, Standard Specification for Polyethylene (PE) Plastic Pipe (DR-PR) Based on Controlled Outside Diameter.

ASTM F-714-03, Standard Specification for Polyethylene (PE) Plastic Pipe (SDR-PR) Based on Outside Diameter.

PRESSURE RATING 3408			DR7.3 255 PSI			DR9 200 PSI			DR11 160 PSI			DR13.5 128 PSI			Pressure Rate
PRESSURE RATING 4710			DR7.3 320 PSI			DR9 252 PSI			DR11 202 PSI			DR13.5 160 PSI			
IPS Pipe Size(In)	Nominal OD (in)	Nominal OD (mm)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	IPS Pipe Size(In)
1/2	0.84	21.34	0.120	0.590	0.12	0.093	0.640	0.10	0.076	0.680	0.08	0.062	0.710	0.07	1/2
3/4"	1.05	26.67	0.150	0.732	0.18	0.117	0.802	0.15	0.095	0.849	0.12	0.078	0.885	0.10	3/4"
1"	1.32	33.40	0.188	0.916	0.29	0.146	1.005	0.23	0.120	1.061	0.20	0.097	1.109	0.16	1"
1 1/4"	1.66	42.16	0.227	1.179	0.44	0.184	1.270	0.37	0.151	1.340	0.31	0.123	1.399	0.26	1 1/4"
1 1/2"	1.90	48.26	0.260	1.349	0.58	0.211	1.453	0.49	0.173	1.533	0.41	0.141	1.601	0.34	1 1/2"
2"	2.38	60.33	0.325	1.686	0.91	0.264	1.815	0.76	0.216	1.917	0.64	0.176	2.002	0.53	2"
3"	3.50	88.90	0.479	2.485	1.98	0.389	2.675	1.66	0.318	2.826	1.39	0.259	2.951	1.15	3"
4"	4.50	114.30	0.616	3.194	3.27	0.500	3.440	2.74	0.409	3.633	2.29	0.333	3.794	1.90	4"
5"	5.56	141.30	0.762	3.948	5.00	0.618	4.253	4.18	0.506	4.490	3.51	0.412	4.690	2.91	5"
6"	6.63	168.28	0.908	4.700	7.09	0.736	5.065	5.93	0.602	5.349	4.97	0.491	5.584	4.13	6"
8"	8.63	219.08	1.182	6.119	12.01	0.958	6.594	10.05	0.784	6.963	8.42	0.639	7.270	7.00	8"
10"	10.75	273.05	1.473	7.627	18.66	1.194	8.219	15.61	0.977	8.679	13.09	0.796	9.062	10.87	10"
12"	12.75	323.85	1.747	9.046	26.25	1.417	9.746	21.97	1.159	10.293	18.41	0.944	10.749	15.29	12"
14"	14.00	355.60	1.918	9.934	31.64	1.556	10.701	26.50	1.273	11.301	22.20	1.037	11.802	18.44	14"
16"	16.00	406.40	2.192	11.353	41.33	1.778	12.231	34.60	1.455	12.915	29.00	1.185	13.488	24.09	16"
18"	18.00	457.20	2.466	12.772	52.31	2.000	13.760	43.79	1.636	14.532	36.69	1.333	15.174	30.48	18"
20"	20.00	508.00	2.740	14.191	64.58	2.222	15.829	54.05	1.818	16.146	45.30	1.481	16.860	37.63	20"
22"	22.00	558.80	3.014	15.610	78.14	2.444	16.819	65.40	2.000	17.760	54.82	1.630	18.544	45.56	22"
24"	24.00	609.60	3.288	17.029	93.00	2.667	18.346	77.85	2.182	19.374	65.24	1.778	20.231	54.21	24"
26"	26.00	660.40	-	-	-	2.889	19.875	91.36	2.364	20.988	76.57	1.926	21.917	63.62	26"
28"	28.00	711.20	-	-	-	3.111	21.405	105.95	2.545	22.605	88.78	2.074	23.603	73.78	28"
30"	30.00	762.00	-	-	-	3.333	22.934	121.62	2.727	24.219	101.92	2.222	25.289	84.69	30"
32"	32.00	812.80	-	-	-	-	-	-	2.909	25.833	115.97	2.370	26.976	96.35	32"
34"	34.00	863.60	-	-	-	-	-	-	3.091	27.447	130.93	2.519	28.660	108.81	34"
36"	36.00	914.40	-	-	-	-	-	-	3.273	29.061	146.80	2.667	30.346	121.98	36"
42"	42.00	1066.80	-	-	-	-	-	-	-	-	-	3.111	35.405	166.00	42"

Pressure Ratings are calculated using 0.63 design factor for HDS at 73°F as listed in PPI TR-4 for PE 4710 materials. HDPE can accommodate up to 1.5 times the pipe pressure rating for a recurring surge and up to 2.0 times the pipe pressure rating for an occasional surge. Temperature, Chemical, and Environmental use considerations may require use of additional design factors.



Iron Pipe Size (IPS) and Dimension Data

ASTM D-3035-03, Standard Specification for Polyethylene (PE) Plastic Pipe (DR-PR) Based on Controlled Outside Diameter.

ASTM F-714-03, Standard Specification for Polyethylene (PE) Plastic Pipe (SDR-PR) Based on Outside Diameter.

PRESSURE RATING 3408			DR17 100 PSI			DR21 80 PSI			DR26 65 PSI			DR32.5 50 PSI			Pressure Rate
PRESSURE RATING 4710			DR17 125 PSI			DR21 100 PSI			DR26 80 PSI			DR32.5 63 PSI			
IPS Pipe Size(In)	Nominal OD (in)	Nominal OD (mm)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	Minimum Wall (in)	Average ID (in)	Weight (lbs/ft)	IPS Pipe Size(In)
1/2	0.84	21.34	0.062	0.710	0.10	0.062	0.716	0.07	0.062	0.710	0.07	0.062	0.710	0.07	1/2
3/4"	1.05	26.67	0.062	0.920	0.12	0.062	0.926	0.08	0.062	0.920	0.08	0.062	0.920	0.08	3/4"
1"	1.32	33.40	0.077	1.150	0.19	0.062	1.191	0.11	0.062	1.180	0.11	0.062	1.180	0.11	1"
1 1/4"	1.66	42.16	0.098	1.444	0.30	0.079	1.502	0.17	0.064	1.532	0.14	0.062	1.180	0.13	1 1/4"
1 1/2"	1.90	48.26	0.112	1.656	0.47	0.090	1.720	0.26	0.073	1.754	0.18	0.062	1.776	0.15	1 1/2"
2"	2.38	60.33	0.140	2.075	0.64	0.113	2.149	0.40	0.091	2.193	0.28	0.073	2.229	0.23	2"
3"	3.50	88.90	0.206	3.063	1.38	0.167	3.166	0.83	0.135	3.230	0.62	0.108	3.284	0.50	3"
4"	4.50	114.30	0.265	3.938	2.29	0.214	4.046	1.26	0.173	4.154	1.02	0.138	4.224	0.82	4"
5"	5.56	141.30	0.327	4.870	3.50	0.265	5.001	1.93	0.214	5.109	1.57	0.171	5.221	1.26	5"
6"	6.63	168.28	0.390	5.798	4.97	0.315	5.957	2.73	0.255	6.084	2.23	0.204	6.193	1.80	6"
8"	8.63	219.08	0.507	7.550	8.41	0.411	7.754	4.64	0.332	7.921	3.79	0.265	8.063	3.05	8"
10"	10.75	273.05	0.632	9.410	13.06	0.512	9.665	7.21	0.413	9.874	5.87	0.331	10.048	4.75	10"
12"	12.75	323.85	0.750	11.160	18.39	0.607	11.463	10.13	0.490	11.711	8.26	0.392	11.919	6.67	12"
14"	14.00	355.60	0.824	12.253	22.19	0.667	12.586	12.22	0.538	12.859	9.96	0.431	13.086	8.05	14"
16"	16.00	406.40	0.941	14.005	28.96	0.762	14.385	15.96	0.615	14.696	13.01	0.492	14.957	10.50	16"
18"	18.00	457.20	1.059	15.755	36.66	0.857	16.183	20.19	0.692	16.533	16.47	0.554	16.826	13.30	18"
20"	20.00	508.00	1.176	17.507	45.25	0.952	17.982	24.93	0.769	18.370	20.34	0.615	18.696	16.41	20"
22"	22.00	558.80	1.294	19.257	54.76	1.048	19.778	30.18	0.846	20.206	24.61	0.677	20.565	19.86	22"
24"	24.00	609.60	1.412	21.007	65.19	1.143	21.577	35.91	0.923	22.043	29.30	0.738	22.435	23.62	24"
26"	26.00	660.40	1.529	22.759	76.47	1.238	23.375	42.14	1.000	23.880	34.39	0.800	24.304	27.74	26"
28"	28.00	711.20	1.647	24.508	88.71	1.333	25.174	48.86	1.077	25.717	39.88	0.862	26.173	32.19	28"
30"	30.00	762.00	1.765	26.258	101.85	1.429	26.971	56.12	1.154	27.554	45.78	0.923	28.043	36.93	30"
32"	32.00	812.80	1.882	28.010	115.86	1.524	28.769	63.84	1.231	29.390	52.10	0.985	29.912	42.04	32"
34"	34.00	863.60	2.000	29.760	130.81	1.619	30.568	72.06	1.308	31.227	58.81	1.046	31.782	47.43	34"
36"	36.00	914.40	2.118	31.510	146.67	1.714	32.366	80.78	1.385	33.064	65.94	1.108	33.651	53.20	36"
42"	42.00	1066.80	2.471	36.761	199.63	2.000	37.760	109.97	1.615	38.576	89.71	1.292	39.261	72.37	42"
48"	48.00	1219.20	2.824	42.013	260.74	2.286	43.154	143.65	1.846	44.086	117.18	1.477	44.869	94.56	48"
54"	54.00	1371.60	-	-	-	2.571	48.549	181.75	2.077	49.597	148.33	1.662	50.477	119.70	54"
63"	63.00	1600.20	-	-	-	3.000	56.640	247.42	2.423	57.863	201.88	1.938	58.891	162.84	63"
65"	65.00	1651.00	-	-	-	3.095	58.810	263.38	2.500	60.000	214.91	2.000	61.000	173.39	65"

Pressure Ratings are calculated using 0.63 design factor for HDS at 73°F as listed in PPI TR-4 for PE 4710 materials. HDPE can accommodate up to 1.5 times the pipe pressure rating for a recurring surge and up to 2.0 times the pipe pressure rating for an occasional surge. Temperature, Chemical, and Environmental use considerations may require use of additional design factors.